



KONUS KONEX d.o.o. - PE KOFIL,  
Mestni trg 18, 3210 SLOVENSKE KONJICE, SLOVENIA

Tel.: ++ 386 03 5753 812, 7573 100; Fax: ++ 386 03 5754 368, 5754 140; E-mail: info@konus-konex.si

QUALITY STANDARD **KOFIL**



**PRODUCT:**

**KOFIL F 5/100**

CHARACTERISTIC:	VALUE:	MEASURE UNIT:	CONTROL METHOD:
Chemical composition	100 % Polyester (heat set)		
Weight	100	g/m <sup>2</sup>	A 23388
Thickness	5	mm	A 23388
Colour	WHITE		
Filter class	EU2 G2		DIN 24185 EN 779
Temperature resistance	70 - 90	°C	
Holding of synthetic dust parts (A)	75	%	DIN 24185
Efficiency on atmospheric dust (E)	-	%	DIN 24185
Air velocity	1,5	m/s	DIN 24185
Initial pressure drop	20	Pa	
Final pressure drop (recommendable)	200	Pa	
Dust holding capacity	360	g/m <sup>2</sup>	
Flame retardant	F1 (selfextinguished)		DIN 53438

Signature:

Date: 16.06.2005